



TECHNICAL PAINT SERVICES

A134 IDENTIFICATION SECURITY PAINT

Features:

A security marking paint for any surface, containing a specially coated dye, which is specifically made for each individual customer. The dry paint film appears normal, but when treated with a strong solvent, releases a custom coloured dye to prove ownership. Also available in quick drying grade (A133).

Availability:

25 Litre minimum lots per colour. Supplied in 5 Litre containers.

Volume Solids:

53% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Ferrous metals and wood should be primed using AP79 Universal Primer before application of A134. Aluminium and alloys should be treated with UP89 Two Pack Etching Primer before application of A134.

Application:

By conventional spray or dipping. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 cup @ 20°C. Use X156 White Spirit for cleaning.

Coverage:

40 sq metres per 5 Litres @ 25 microns dry film thickness.

Drying:

Touch dry: 30 minutes @ 20°C.

Hard dry: 12 hours @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.